



Advanced Technology. Quality Products. Responsive Service.

**USA:**  
**160 Ridgeland Dr., Suite 300**  
**Greenville, SC 29601**  
**Plant: 200 Tanner Dr.**  
**Tailors, SC 29687**  
**(864) 908-6057**

**Honduras:**  
**Building #20, Zip Bufalo**  
**Villanueva, Honduras**  
**Office: 504-2574-9083**  
**Email: excel-products@juno.com**

## **EXTRAPEL FCX**

**EXTRAPEL FCX** is a cationic water repellant and extender for fluorocarbon finishes. It may be pad applied alone onto cellulose and synthetic woven and non woven goods or applied with fluorocarbon finishes to extend their repellant properties.

**EXTRAPEL FCX** is a cross-linking resin and wax emulsion that requires curing to be durable. A minimum curing temperature of 330° F. for 75-90 seconds is recommended.

### **GENERAL PROPERTIES:**

Appearance:	White liquid
Solids:	25 %
Ionic Nature:	Cationic
Solubility:	Easily soluble in water
Product Stability:	9 Months to one year at ambient storage temperatures

### **APPLICATION:**

4-10% owb is recommended if **EXTRAPEL FCX** is used alone.

3-5% owb **EXTRAPEL FCX** is recommended in combination with fluorocarbon finishes.

All data discussed herein are believed to be correct. However, this should not be accepted as a guarantee of their accuracy and confirming tests should be run in your own plant or laboratory. No statement should be construed as a recommendation for any use which would violate any patent right. Nothing contained herein shall constitute a guarantee or warranty with respect to the products described or their use.